SUBMITTAL-Commercial Grade

RED RUBBER Style AB-619 Manufacturer – American Biltrite

Gaskets meet the pressure ratings, drilling and dimensions of ANSI/ASME B16.2.1

Style AB-619

SBR (Red)

Media

- Cold and Hot Water
- Air
- Steam
- Some weak Acids

Specifications

Max. Temperature:	200	(° F)
Hardness Shore A	75	
Tensile Strength ASTM D-412	600	(PSI)
Elongation	200 %	

Availability



Benefits

- An economical, non-oil resistant compound that resists flow under compression.
- Offers moderate to good performance against low pressure and good aging, abrasion and tear resistance.
- Easily conforms to uneven flange surfaces.





475 Klug Circle-Corona, CA. 92880 (951) 280-4488 - Fax: (951) 272-4445