



Gasketed Pipe

PIP Size

Submittal and Data Sheet

PIP Pressure-Rated PVC

November 1998

Gasketed P.R. 63 - SDR 64

Nominal Pipe Size (inches)	Average Outside Diameter (inches)	Approximate Inside Diameter (inches)	Minimum Wall Thickness (inches)	Approximate Weight (lbs/100')	Length per Crate (feet)	Approximate Crate Weight (lbs)
15	15.300	14.78	0.239	769	120	923
18	18.701	18.07	0.292	1151	40 / 60	461 / 691

Gasketed P.R. 80 - SDR 51

Conforms to: ASAE S376.1, ASTM D 2241 (15"-24") and SCS 430DD

Nominal Pipe Size (inches)	Average Outside Diameter (inches)	Approximate Inside Diameter (inches)	Minimum Wall Thickness (inches)	Approximate Weight (lbs/100')	Length per Crate (feet)	Approximate Crate Weight (lbs)
6	6.140	5.88	0.120	154	520	803
8	8.160	7.81	0.160	273	300	820
10	10.200	9.77	0.200	427	240	1026
12	12.240	11.72	0.240	615	160	984
15	15.300	14.65	0.300	961	120	1154
18	18.701	17.91	0.367	1437	40 / 60	575 / 862
21	22.047	21.12	0.432	1994	40	798
24	24.803	23.76	0.486	2524	40	1010

Gasketed P.R. 100 - SDR 41

Conforms to: ASAE S376.1, ASTM D 2241 (15"-24") and SCS 430DD

Nominal Pipe Size (inches)	Average Outside Diameter (inches)	Approximate Inside Diameter (inches)	Minimum Wall Thickness (inches)	Approximate Weight (lbs/100')	Length per Crate (feet)	Approximate Crate Weight (lbs)
6	6.140	5.81	0.150	192	520	998
8	8.160	7.73	0.199	338	300	1014
10	10.200	9.66	0.249	529	240	1270
12	12.240	11.60	0.299	762	160	1219
15	15.300	14.50	0.373	1189	120	1427
18	18.701	17.72	0.456	1777	40/60	711 / 1066
21	22.047	20.89	0.538	2471	40	988
24	24.803	23.50	0.605	3135	40	1254

Gasketed P.R. 125 - SDR 32.5

Conforms to: ASAE S376.1 (18"-24"), ASTM D 2241 (15"-24") and SCS 430DD

Nominal Pipe Size (inches)	Average Outside Diameter (inches)	Approximate Inside Diameter (inches)	Minimum Wall Thickness (inches)	Approximate Weight (lbs/100')	Length per Crate (feet)	Approximate Crate Weight (lbs)
6	6.140	5.73	0.189	240	520	1250
8	8.160	7.62	0.251	424	300	1272
10	10.200	9.52	0.314	665	240	1596
12	12.240	11.43	0.377	960	160	1536
15	15.300	14.29	0.471	1492	120	1790
18	18.701	17.47	0.575	2226	40 / 60	890 / 1336
21	22.047	20.59	0.678	3094	40	1238
24	24.803	23.17	0.763	3917	40	1567

General Notes:

1. Pipe material conforms to ASTM D 1784 cell class 12454.
2. Gaskets meet the requirements of ASTM F 477.
3. Pipe is produced with integral gasketed bells in 20 foot laying lengths.
4. Inside diameters may vary due to allowable manufacturing tolerances.
5. Approximate weights are for estimating purposes only.
6. All orders are subject to final acceptance at the Eugene office.