ROMAC INDUSTRIES, INC.

STYLE 501 AND RC 501 REDUCING COUPLING

SUBMITTAL INFORMATION

AWWA C219 Romac 501 couplings meet the specifications set forth

in the AWWA Standard C219 coupling spec.

MATERIALS

Castings The end rings and center rings are cast from ductile

(nodular) iron, meeting or exceeding ASTM A 536.

Gaskets Gaskets are made from virgin Styrene Butadiene

Rubber (SBR) compounded for water and sewer service in accordance with ASTM D 2000 MBA 710. Other compounds available for petroleum, chemical, or high

temperature service.

Bolts and Nuts 5/8 inch, High strength low alloy steel trackhead bolts.

National coarse rolled thread and heavy hex nuts. Steel meets AWWA C111 composition specifications. Stainless steel bolts and nuts available on request.

Coatings Shop coat applied to cast parts for corrosion

protection in transit. Fusion bonded epoxy, liquid epoxy and other coatings available on request.

PRESSURE When properly installed on a pipe that is within the

correct outside diameter range, couplings in the Romac Style 501 line can be used at working pressures up to 260 psi. Higher working pressures

available for specific applications.

SIZES AND RANGES See Catalog. 4/08

Romac Document Number 20-8-0005

This information is based on the best data available at the date printed above, please check with Romac Engineering Department for any updates or changes.